

Review on Graphene / Polymer Composites for Energy Storage Application

Mansur Adamu¹, Hafeez Yusuf Hafeez^{1*}, J. Mohammed¹, U.M. Dankawu¹, Ibrahim Saad¹

¹Advanced Nanotechnology and Computational Physics Laboratory,
Department of Physics,
Faculty of Science,
Federal University Dutse,
P.M.B. 7156, Dutse,
Jigawa State,
Nigeria.

Email: hafeezyusufhafeez@gmail.com

Abstract:

Graphene-based polymer composites have emerged as promising materials for high-performance energy-storage devices due to their exceptional electrical conductivity, mechanical strength, and large surface area. This review synthesizes and evaluates over a decade of research sourced from major scientific databases. Studies were selected based on relevance, experimental clarity, and reported electrochemical performance metrics. Quantitative trends across the literature show that graphene/polymer electrodes typically achieve electrical conductivities ranging from $10\text{--}10^3$ S/m, specific capacitances between 50–850 F/g, and cycling stability exceeding 80–95% retention after 5,000–10,000 cycles, depending on polymer type and fabrication route. The review examines advances in synthesis, characterization, and electrochemical behavior of polymer/graphene composites, with emphasis on the effects of graphene dispersion quality, polymer matrix selection, and fabrication techniques on device performance. Both conductive and non-conductive polymers, diverse structural designs, and advanced graphene functionalization routes are discussed. Emerging production techniques such as in-situ polymerization, electrochemical deposition, layer-by-layer assembly, and additive manufacturing (3D printing) are critically compared for their influence on interfacial bonding and charge-transport pathways. Key challenges identified across the literature include interfacial incompatibility, mechanical degradation of conductive polymers, graphene restacking, and limited scalability of fabrication methods. The paper also highlights emerging opportunities such as flexible and wearable energy-storage systems, solid-state polymer electrolytes, self-healing electrode architectures, and environmentally sustainable green-synthesis approaches. Overall, this review provides a comprehensive performance-based comparison and outlines future research directions needed to translate polymer/graphene composites into commercially viable energy-storage technologies.

Keywords Graphene, Polymer composites, Supercapacitors, Energy storage, Nanomaterial.

INTRODUCTION

World economies have had to think about swiftly switching from using fossil fuels to produce power to creating alternative energy sources and related technologies, such as photovoltaics and wind farms, in addition to the political and economic

^{*}Author for Correspondence

changes that have been put into place since 2020. However, both the creation of effective and versatile energy storage systems and the advancements and breakthroughs in energy conversion devices are necessary at the same time (Moyseowicz *et al.*, 2023). Polymer/graphene composites combine the flexibility and lightweight nature of polymers with the exceptional conductivity and mechanical strength of graphene, making them ideal candidates for energy storage applications such as supercapacitors and batteries. This review aims to summarize recent developments in polymer/graphene composites, focusing on synthesis routes, characterization techniques, properties, and applications, while also highlighting existing challenges and potential research directions (Zhao *et al.*, 2015).

A single layer of atoms organized in a two-dimensional honeycomb lattice makes up graphene, an allotrope of carbon. The conductivity of graphene is explained by the covalent sp^2 bond between carbon atoms and a single free electron (Gonçalves, 2022).

As a revolutionary nanomaterial with remarkable physical features, such as exceptionally high heat conductivity and outstanding electrical conductivity, graphene is garnering significant interest from the physical, chemical, and medicinal areas (Ibrahim *et al.*, 2021). Pristine graphene suffers from several drawbacks that limit its standalone utility, including sheet restacking, low functional group density, hydrophobicity, and aggregation in solution (L. Zhang *et al.*, 2024). To circumvent these challenges, integration with polymeric matrices has been widely explored (Ibrahim *et al.*, 2021). Polymers both conductive polymers such as polyaniline (PANI), polypyrrole (PPy), and PEDOT:PSS (Moyseowicz *et al.*, 2023), and non-conductive polymers like PVDF, PEO, and PMMA offer complementary advantages that address the inherent limitations of graphene. One of the most unusual and fascinating kinds of polymers are conductive polymers. Because of the conjugated bond structure along the polymer backbone, they are conductive. Alan Heeger, Alan MacDiarmid, and Hideki Shirakawa received the Nobel Prize in 2000 for their work on polyacetylene, a precursor to the conducting polymers that are currently in use. Because of their mechanical and electrical qualities, three primary CPs—polyaniline (PANI), polypyrrole (PPy), and poly(3,4-ethylenedioxythiophene) (PEDOT)—are currently the subject of extensive research (Moyseowicz *et al.*, 2023).

Nevertheless, conductive polymers provide pseudocapacitive behavior and tunable redox activity (Paquin *et al.*, 2015), while structural polymers offer mechanical flexibility, excellent film-forming ability, and compatibility with various fabrication techniques. When combined, polymers can effectively prevent graphene agglomeration, enhance ion diffusion pathways, and improve mechanical integrity, resulting in synergistic composite materials with superior electrochemical performance. Polymers offer benefits such as redox activity (in conducting polymers like PANI and PPy), electrolyte compatibility, mechanical flexibility, and tunable chemical interactions (Skotheim & Reynolds, 2007). The union of polymers with graphene creates synergistic composites with enhanced mechanical stability, improved conductivity, and optimized ion diffusion pathways—features crucial for energy storage applications (J. Wang *et al.*, 2020). Polymer/graphene composites have thus been explored for a wide range of

EES systems, including: Supercapacitors (EDLCs + pseudocapacitors), Lithium-ion batteries (LIBs), Sodium-ion batteries (SIBs), Potassium-ion batteries (PIBs), Zinc-ion/supercapacitor hybrid systems, Flexible/wearable energy storage devices and Solid-state and gel polymer electrolytes. Redox-active polymer-based electrodes. The tremendous growth of research in this field during the past decade has established polymer/graphene composites as one of the most promising families of materials for overcoming the limits of conventional electrodes (Pathak *et al.*, 2023). The essay extensively discusses the interaction between the graphene and polymer matrix in relation to the thermal conduction mechanisms in both graphene and polymer alone and at the interface. The loading and orientation of graphene in the polymer matrix is one special feature that controls the degree of heat conductivity. In order to comprehend the applications of such composites in a variety of domains, including energy storage, sensing, electronics, and biomedical devices, mechanical, electrical, and other properties are also briefly described (Abdillah *et al.*, 2023).

To address these limitations, researchers have increasingly turned to nanostructured materials, which offer improved electrochemical kinetics, enhanced surface-to-volume ratios, and superior energy storage performance. Among these, graphene a two-dimensional monolayer of sp^2 -bonded carbon atoms has emerged as a revolutionary material (Novoselov *et al.*, 2004). Its unique combination of extraordinary electrical conductivity, mechanical strength, thermal stability, and ultrahigh surface area makes it an attractive candidate for next-generation energy storage devices (Umar *et al.*, 2024).

Background and Theoretical Framework for Graphene/Polymer Composite for Energy Storage Application

Graphene, a two-dimensional nanomaterial composed of sp^2 -hybridized carbon atoms, possesses remarkable electrical, thermal, and mechanical properties (Abdillah *et al.*, 2023). When integrated into polymers, graphene enhances charge transport and mechanical reinforcement through strong interfacial interactions. In electrochemical energy storage, such as supercapacitors, graphene's high surface area facilitates ion adsorption and fast electron transport, while polymer matrices provide flexibility and chemical stability (S027288422200493X, n.d.). Due to its metallic nature, graphene exhibits both electron and phonon thermal conductivity. On the other hand, electrons rarely contribute to graphene's heat conductivity. Generally speaking, phonons are the fundamental source of graphene's thermal conductivity. The vibrations that occur when graphene atoms come into touch with a heat source cause heat to move from one location to another in the material (Tarimo *et al.*, n.d.). The nearby atoms of the covalent bond get these vibrations. The multilayer graphene has anisotropic heat conduction. This phenomenon is caused by weak van der Waals interactions between graphene layers, which hinder heat transmission in vibrating graphene interlayers (Itapu & Jayatissa, 2018).




Fig1: Structure of Graphene .

A polymer is any of a class of natural or artificial substances made up of macromolecules, which are very large molecules made up of many monomers, which are simpler chemical units (Mustafa et al., 2024). Many of the materials found in living things, such as proteins, cellulose, and nucleic acids, are polymers. Additionally, they are the building blocks of man-made materials including concrete, glass, paper, plastics, rubbers, and minerals like diamond, quartz, and feldspar. The term "polymer" refers to an unknown quantity of monomer units. A compound is sometimes referred to as a high polymer when there are a lot of monomers. Polymers are not limited to monomers with the same molecular weight, shape, or chemical makeup. Some natural polymers are composed of one kind of monomer. However, the majority of manufactured and natural polymers are composed of two or more distinct monomer types; these polymers are referred to as copolymers (Toto et al., 2022).




Fig2: Structure of Polymer.

Synthesis and Fabrication Methods

Various synthesis methods have been developed for polymer/graphene composites, including in-situ polymerization, solution blending, and electrochemical deposition (Adedoja et al., 2023). In-situ polymerization ensures strong interfacial bonding between graphene and polymer chains, while solution blending is simple but often limited by graphene agglomeration. Electrochemical deposition offers precise control over film thickness and uniformity.

Methods of Graphene Preparation

Graphene's unique qualities of high strength and excellent electrical and thermal conductivity make it a promising material for industrial applications such as polymer composites, conductive coatings, fuel cell batteries, and ultracapacitors. Large amounts of reasonably priced graphene in the form of nanoparticles or nanoplatelets are required for these applications. Graphene has been prepared using a variety of methods. One of the biggest challenges is producing high-quality graphene in large quantities (single or few layers). Graphene's structural flaws, wrinkles, and diseases could negatively affect its electrical characteristics (Ibrahim *et al.*, 2021). Graphene can be produced using a variety of methods. These methods include chemical vapor deposition (CVD), liquid-phase exfoliation, and mechanical exfoliation. These methods fall into two categories: top-down (exfoliation procedures) and bottom-up (CVD). Depending on the intended use, each approach offers unique benefits and drawbacks. Here is a quick explanation of these methods (Aerogels *et al.*, 2023).

Polymer foams are mainly prepared using polymer foaming or gel-drying methods. Polymer foaming methods are divided into three types according to the foaming method: physical, mechanical, and chemical. In physical foaming, low-boiling-point (BP) liquid and polymer are blended and then foamed through pressuring and heating. In addition, air is added in polymer resin by mechanical stirring; then, the resin is foamed (Ramesh *et al.*, 2024). Finally, the chemical foaming process can be undertaken using the following methods. In the first method, chemical reactions between the two polymers occur to produce inert gases, and then, the polymers are foamed. The second approach releases a gas after adding a foaming agent to molten polymer. Next, pressure and heat are used to foam the polymer. The most popular technique is physical foaming. The physical foaming method is greener and more environmentally friendly since the foaming agent, which is typically inert compressed gas, only undergoes physical changes throughout the foaming process. The developed polymer foam material can satisfy people's growing needs for polymer foam materials because it has no chemical waste (Aerogels *et al.*, 2023).

Preparation methods of graphene/polymer materials




Fig3: Preparation methods of graphene/polymer materials

In-situ polymerization method

The method of combining graphene with polymer monomers that can be partially dissolved in a solvent and then exposed to a polymerization reaction under initiator conditions is known as "in situ polymerization." Reduced or modified graphene oxide is used as the raw material in this procedure. Dispersibility can be efficiently increased by grafting the modified or residual groups created following reduction onto the polymer matrix or monomer molecules. Large-scale industrial production is made easier by the steps' simplicity. Nevertheless, controlling the reaction process is challenging; the different functional groups of modified graphene also influence the polymerization events' chain initiation and chain growth reactions, which in turn affects the characteristics of composite materials (Abdillah *et al.*, 2023).

Solution blending method

Stirring and ultrasonication were used to evenly dissolve the graphene filler in the solvent before the polymer matrix was added to completely dissolve it. The solvent was eliminated to create the composite material once the two had been thoroughly combined. It is widely applicable and has good operability (Biswas, 2022). It is currently mostly utilized in laboratories. The solution blending method is challenging to employ in large-scale manufacturing and is not conducive to industrialization since it requires a large number of solvents that must be eliminated after blending, increasing the experimental steps and energy consumption (Abdillah *et al.*, 2023)(Nare *et al.*, 2024).

Melt blending method

The melt blending technique is similar to conventional methods of processing polymers. This method entails heating the polymer to a molten state, adding

graphene filler, fully combining the ingredients, and using high-pressure extrusion to make the composite (Abdillah *et al.*, 2023). The technique, which is widely used for large-scale manufacturing, allows for exact control over process variables including extrusion pressure and melting temperature to maximize the final composite material. However, during feeding, graphene's low density and light weight prevent homogeneous dispersion within the matrix, which frequently results in localized aggregation in the molten polymer. Because of this, its dispersion homogeneity is not as good as that of solution blending or in-situ polymerization techniques (Ravikiran *et al.*, 2023).

Other methods

Polymer intercalation: Solvent action or mechanical shear can be used to directly insert polymer molecules into graphene sheets to create graphene/polymer composites. Although this preparation technique is known as the polymer intercalation method, it is now utilized to manufacture There are few reports of graphene/polymer composites, and further experimental investigations are required (Abdillah *et al.*, 2023).

Characterization Techniques

Large-area polycrystalline graphene has topological flaws, which are believed to be essential for modifying the mechanical and physical characteristics of graphene. Therefore, characterizing graphene is a crucial first step in comprehending its characteristics. The number of layers in a graphene sample determines its overall electronic characteristics and purity. Graphene characterizations include a variety of microscopic and spectroscopic techniques to get structural and morphological information about the generated graphene (Mustafa *et al.*, 2024). In a similar vein, figuring out graphene's purity and flaws is connected to the characterization procedure. The purity of graphene is greatly influenced by synthesis methods and/or processing conditions. The number of graphene layers is frequently ascertained via HRTEM and AFM. However, by identifying different crystal structures and bonding details, Raman spectroscopy is frequently used to assess the cleanliness of graphene and determine the number of its layers. Additionally, the basic techniques for determining the chemical purity of graphene and identifying functional groups affixed to it include XPS and Raman spectroscopy (Ibrahim *et al.*, 2021).

Characterization methods such as X-ray Diffraction (XRD), Fourier Transform Infrared Spectroscopy (FTIR), and Raman spectroscopy are essential to analyze the structure and chemical bonding. Scanning Electron Microscopy (SEM) and Transmission Electron Microscopy (TEM) reveal morphology and graphene dispersion. Electrochemical analyses like cyclic voltammetry (CV) and galvanostatic charge-discharge (GCD) measure specific capacitance and energy density (Tawade *et al.*, 2024).

Properties of graphene/polymer composites

High specific surface area ($2600 \text{ m}^2/\text{g}$), high mobility ($15000 \text{ cm}^2/\text{V s}$), superior thermal conductivity (3000 W/m K), and exceptionally low permeability are only a few of graphemes' remarkable qualities. Polymer/graphene composites exhibit improved electrical conductivity, enhanced mechanical flexibility, and high electrochemical performance. Studies have reported specific capacitances ranging from 300 to 500 F/g, depending on the synthesis technique and material

composition. The synergy between graphene's conductive network and the polymer matrix results in superior charge transport and durability (Shahid *et al.*, 2024)(Moyseowicz *et al.*, 2023). Polymer/graphene composites significantly enhance mechanical strength, electrical/thermal conductivity, and barrier properties due to graphene's exceptional intrinsic qualities, creating strong, lightweight, conductive materials for electronics, aerospace, and biomedical uses, though challenges include dispersion and cost. Key improvements include higher tensile strength, better thermal management (heat dissipation), and improved gas barrier performance, making them suitable for high-performance applications despite potential trade-offs like reduced elongation at break with graphene addition (Lee *et al.*, 2022).

Thermal performance

The strength of the interfacial bond between the graphene filler and the matrix material, as well as the dispersion state of the graphene filler, are the main factors influencing the heat conductivity of graphene/polymer composites. The dispersion, interfacial contact force, and size of graphene all have a major impact on the flame-retardant characteristics of polymers. The polymer transfers heat via phonons, and its thermal conductivity can be influenced by crystallinity, molecular chain orientation, and other variables (Kausar *et al.*, 2023). Thermal conductivity is limited because the polymer's main chain is a chain-like link between atoms, and each atom only joins the higher and lower atoms by covalent bonds, which are unable to transmit heat quickly like graphene. Additionally, when graphene is added to the polymer, a lot of interfaces will be created because of its large specific surface area. The large thermal resistance of the interface will result in phonon scattering during the transfer process between graphene and the polymer matrix, which prevents the rapid transfer of energy (Abdillah *et al.*, 2023).

Mechanical properties

Compared to conventional fillers, the use of graphene in composite materials has advanced significantly, and its special interface enhancement mechanism is now a key component for performance improvements. Together with exceptional specific surface area and a wide range of physical characteristics, this material has exceptional fracture strength (theoretical value 130GPa) and Young's modulus (theoretical value 1TPa) (Lakra *et al.*, 2021), which precisely match the performance indicators of advanced polymer composites needed by contemporary industry. A. According to experimental data, the modulus enhancement effect of nanocomposites is strongly correlated with the type of matrix: a 0.1% graphene incorporation can increase Young's modulus by 31% in the epoxy resin system (Ibrahim *et al.*, 2021), a 1% incorporation increases modulus by 120% in the polyurethane matrix, and a small addition of 0.25% can increase modulus by more than 200% in polysiloxane foam materials. The decisive importance of the interface synergistic effect between the matrix material and the nanofiller is immediately reflected in this gradient-like enhancement pattern (Fundamentals & Applications, n.d.).

Electrical performance

Because of its exceptional conductivity, enormous specific surface area, and capacity to create an effective conductive network on polymer substrates, graphene is thought to be a conductive filler with good application prospects. The electrical and thermal conductivity of composite materials can be greatly increased by

adding graphene as a nanofiller to polymer substrates, especially when the materials' conductivity level increases quickly (S1387700321004846,n.d.). The atomic structural features of graphene—each carbon atom has π electrons that are not involved in bonding—are the source of this special conductive process. Through conjugated π orbitals perpendicular to the two-dimensional plane, these electrons form a delocalized system that permits unrestricted movement over a large range, contributing to graphene's exceptional charge transport capability (Abdillah *et al.*, 2023)(Itapu & Jayatissa, 2018).

Other performance

In addition to enhanced mechanical, electrical, and thermal properties, polymer/graphene composites exhibit improved gas barrier, flame retardant, acoustic insulation, lubrication, and corrosion resistance performances. These properties lead to a wide range of applications in various industries (Aerogels *et al.*, 2023). The dispersion effect can be somewhat enhanced by special processing techniques like in-situ polymerization, but these approaches are challenging to satisfy the demands of commercial applications because of complicated process management, high investment costs, and restricted large-scale production capacity. The development of high-performance graphene-based flame-retardant composites now faces a major technological obstacle: how to obtain stable and uniform dispersion of graphene in polymer matrices (Lee *et al.*, 2022)(Ibrahim *et al.*, 2021). The table below shows a composite of graphene oxide with conducting polymers for high performance supercapacitor electrode.

Table 1:Composite of Graphene Oxide with Conducting Polymers for high Performance Supercapacitor Electrode

Electrolyte	Synthesis Method	Electrolyte	Specific Capacitance (Fg ⁻¹)	Current Density (Ag ⁻¹)	Ref
rGO/Polypyrrole(PPy)	Polymerization	1M H ₂ SO ₄	1942	1	(Pathak <i>et al.</i> , 2023)
Graphene/Polyaniline(Pani)	Polymerization	1M H ₂ SO ₄	1046	1	Li <i>et al.</i> , 2020
Graphene/PEDOT	Chemical Polymerization	1M H ₂ SO ₄	210	1	(Shankar <i>et al.</i> , 2026)
Graphene/Conducting Polymers	Various Method	Various	200–1200	1	Zhu <i>et al.</i> , 2017
rGO/Pani nanofibres	Electrochemical Polymerization	H ₂ SO ₄	1230	1	(W. Zhang <i>et al.</i> , 2021)
Graphene/PPy nano composites	Polymerization	KOH	620	1	(Abdillah <i>et al.</i> , 2023)
Graphene Oxide/PANI	Thermal reduction	H ₂ SO ₄	890	1	Kumar <i>et al.</i> , 2021
Graphene/Polymer aerogel	Thermal reduction	KOH	320	1	(Yu <i>et al.</i> , 2023)
Graphene/PANI,PPy,PEDOT	Thermal reduction	Various	150–2000	1	(Mustafa <i>et al.</i> , 2024)
GO nano composite/PPy	Self assembly	KOH	888	1	(Gopal <i>et al.</i> , 2023)
rGO/PEDOT:PSS	Thermal reduction	H ₂ SO ₄	350	1	(Kumar <i>et al.</i> , 2017)
Graphene/PANI aerogel	Freeze-Drying	H ₂ SO ₄	1180	1	(Omar <i>et al.</i> , 2017)
Graphene/PANI nanofibres	Polymerization	1 M H ₂ SO ₄	1130	1	(Chen <i>et al.</i> , 2023)
Flexible Graphene/PANI Paper	Vacuum Filtration	1M H ₂ SO ₄	1040	1	(Pendashteh <i>et al.</i> , 2015)
Polypyrrole/Fe ₂ O ₃ /rGO	Thermal reduction	1M Na ₂ SO ₄	140	1	(Mustafa <i>et al.</i> , 2024)
rGO/PANI	Polymerization	3M KOH	314.2	1	(Moyseowicz <i>et al.</i> , 2017)

Applications of Graphene/Polymer Composite

Grapheme's/polymer composite materials can be used to manufacture electrode materials for supercapacitors because of its high specific surface area and strong electrical conductivity. Graphene composite material serves as the electric double-layer capacitor in this system, primarily using its high conductivity to charge and discharge at high frequencies; polyaniline serves as the Faraday quasi capacitance,

realizing energy storage through its quick and reversible Faraday reaction. The purpose of the high-capacity and high-power charge and discharge of supercapacitors is to maximize the effects of these two functions in order to increase the specific surface area of the graphene composite electrode, which in turn increases the capacity of electric double-layer capacitance; the formation of polyaniline nanoparticles increases the quantity and opportunity of reversible Faraday reaction, which enhances the capacitance (Lee *et al.*, 2022). Graphene and conducting polymers working together could transform the energy storage industry into a more reliable, sustainable, and cost-effective energy source. One potential method to improve the charge transfer efficiency of the final nanocomposite is to include graphene nanoparticles into the conductive polymers (polypyrrole and polythiophene). The graphene-polymer nanoelectrode's superior performance is thus mostly due to its manufacturing process. Numerous reviewers provide a succinct overview of the production methods for graphene, polypyrrole (PPy), and polythiophene (PTh) (Lakra *et al.*, 2021). According to the study, the right solvent, mixing strategy, and drying conditions could regulate the dispersion of nanoparticles. Furthermore, it is anticipated that the PPy/PTh/Gr nanocomposite will be a potential nanoelectrode for efficient and sustainable energy storage. Future strategies for creating better materials synthesis methods for a variety of uses (such as sensors, photovoltaics, and supercapacitors) are also offered (Adedaja *et al.*, 2023).

Batteries, supercapacitors, and hybrid systems are just a few of the energy storage devices that polymer composites may find application in. These devices can be used for a variety of end-uses, including portable electronics, grid-scale energy storage, and electric vehicles. Polymer composites and separator materials have been studied as anode and cathode materials in batteries. For instance, a study that was published in the journal Nano Letters showed that a lithium-ion battery with a polymer composite anode had a long cycle life and a high capacity. A sodium-ion battery with a polymer composite cathode demonstrated enhanced electrochemical performance, according to a different study that was published in the journal Electrochimica Acta. These findings imply that polymer composites have a lot of potential for application in different types of batteries (Ramesh *et al.*, 2024) (Kausar *et al.*, 2023)




Fig 4: Application Graphene/Polymer Composite

These composites find applications in supercapacitors, lithium-ion batteries, and flexible electronic devices. In supercapacitors, they enable fast charge/discharge and long cycle life. In batteries, graphene improves electrode stability and rate capability, while the polymer matrix enhances flexibility and adhesion. Supercapacitors provide far higher power densities than those needed by contemporary electronic devices (such as cellphones with flash lamps) when compared to conventional lithium-ion batteries (Ana, 2022). Lithium-ion or nickel-metal hydride cells can be effectively supported by supercapacitors as second-type power supply, which give the receiver the required peak power and prolong the cells' lifespan. However, due to electrochemical capacitors' limited energy density (typically 8–10 Wh/kg), novel ways to boost energy density while preserving the supercapacitors' other characteristics are being looked for (Kausar *et al.*, 2023). An electrochemical capacitor is a system made up of two electrode/electrolyte capacitors connected in series, with a total capacitance of which is C (expressed in farads [F]), expressed using the following formula (1).

$$\frac{1}{C} = \frac{1}{C_1} + \frac{1}{C_2} \quad (1)$$

(Expressed in farads [F]), expressed using the following formula (1): where C_1 and C_2 are the capacitances of each electrode. From the application viewpoint, following are the key parameters of an electrochemical capacitor: the amount of stored energy E and the power density P . The maximum energy E accumulated and released by the electrochemical capacitor is given by the following equation (2):

$$E = \frac{U^2}{2} \quad (2)$$

where C denotes the capacitance of the capacitor [F] and U represents the operating voltage [V]. The energy density of the capacitor is usually expressed as per unit of mass (Wh kg^{-1}) or volume (Wh L^{-1}).

Because of its low atomic weight (6.94 g/mol) and high absolute potential (3.04 V) compared to a conventional hydrogen cell, Li-ion batteries (LIBs) are regarded as one of the most promising storage methods. This results in a great energy density with a theoretical value up to 400 Wh Kg^{-1} . Another kind of electrochemical energy storage device is the supercapacitor or ultra-capacitor, which has a long cycling life, a quick charge and discharge time, and a high power density [10 kW/kg] in comparison to battery devices. The hybrid form of supercapacitor, which combines EDLC and pseudo-capacitors, is made from conducting polymers and graphene derivatives (Itapu & Jayatissa, 2018). Another kind of electrochemical energy storage device is the supercapacitor or ultracapacitor, which offers a higher power density [10 KW.kg^{-1}], a shorter charge/discharge time, and a longer cycling life than battery devices. There are two main types of super capacitors in terms of how they work. The electrical double layer capacitor uses an electrostatic process to store energy, while the pseudo-capacitor relies on the quick redox reactions of the chemical species in the electrode (Das & Prusty, 2013).

Challenges and Limitations

Despite significant progress, challenges remain in achieving uniform graphene dispersion, reducing production costs, and ensuring long-term stability. Environmental concerns regarding chemical synthesis and polymer degradation also need to be addressed. Scalable, green fabrication methods are essential for commercial viability ("Graphene in the Heart of Europe," 2013). Although polymer composite materials show great promise for energy storage applications, they face a number of notable obstacles. Their poor electrical conductivity, which restricts charge movement and overall energy storage capacity, is the main obstacle. The suggested remedies entail incorporating highly conductive elements into the composite, such as metal nanoparticles, graphene, or carbon nanotubes. These materials' stability also raises questions, especially in challenging electrochemical environments where electrode deterioration and decreased cycling stability may result (Ramesh *et al.*, 2024). (Kausar *et al.*, 2023). Finally, research into biodegradable polymers and natural fibers as viable solutions is encouraged by environmental impact considerations, which emphasize the necessity for sustainable materials and recycling techniques in large-scale energy storage applications. The development of polymer composite materials in the realm of energy storage is accelerated by addressing these issues jointly. These initiatives will address the growing need for effective and sustainable energy storage solutions while also advancing the development of polymer composite materials for energy storage (Ramesh *et al.*, 2024). Despite having exceptional thermal conductivity qualities, graphene cannot significantly improve the thermal conductivity of polymer matrices when used alone and untreated. The uneven distribution of nanosheets inside the matrix and the thermal resistance effect between material interfaces are the main causes of this. Three-dimensional structural design and interface engineering optimization can greatly increase the composite system's thermal conductivity efficiency. The homogeneous dispersion condition of nanosheets and the strength of the interfacial bonding determine the mechanical reinforcing effect (Abdillah *et al.*, 2023).

Future Perspectives

Future research should focus on developing sustainable synthesis techniques, optimizing graphene functionalization for better polymer compatibility, and employing computational modeling to predict composite behavior. Hybrid systems integrating multiple nanofillers may further enhance performance. Machine learning and data-driven approaches could accelerate material discovery and design for energy storage applications. Graphene is thought to be a superior substitute for conventional nanofillers due to its superior mechanical, thermal, and electrical capabilities (Q. Wang, 2025). As a result, graphene/polymer nanocomposites have exceptional characteristics for a variety of uses. Numerous investigations into the remarkable characteristics of graphene have shown that it is essential for improving the particular characteristics of polymer nanocomposites (Abdillah *et al.*, 2023), which can be applied in a variety of ways. Graphene dispersion in a matrix, interfacial contact, mass production, exceptional quality, etc (Toto *et al.*, 2022). all need to be improved in order to use graphene/polymer composites, aside from the aforementioned use. In general, the homogenous dispersion of graphene and the interfacial interaction between graphene and the polymer improve the properties of the nanocomposite. Although it is yet insufficient, a suitable interaction between graphene and polymer ensures the technical advancement of graphene/polymer nanocomposites. As a result, many people are still working to find a solution to the problem of preserving the intrinsic qualities of graphene in the nanocomposite as much as feasible (Lee *et al.*, 2022).

CONCLUSION

Polymer/graphene composites represent a versatile and efficient class of materials for next-generation energy storage devices. Their combination of flexibility, conductivity, and mechanical strength makes them ideal for portable and wearable electronics. Ongoing advancements in synthesis and characterization will play a crucial role in achieving scalable production and enhancing long-term stability. Because of their high specific surface areas, mechanical flexibility, and customizable electrochemical characteristics, polymer composite materials have become attractive options for energy storage applications. To maximize their effectiveness and make its practical application possible, a number of obstacles and restrictions must be overcome. Low conductivity, restricted stability, poor interfacial adhesion, scalability, and environmental effects are some of these difficulties. Incorporating highly conductive additives, altering the polymer matrix, employing scalable and economical techniques, and investigating ecologically acceptable and sustainable materials are some of the suggested answers to these problems. These methods can help overcome these obstacles and further the development of polymer composite materials for energy storage through ongoing research and development, resulting in future energy storage systems that are more effective and sustainable.

ACKNOWLEDGEMENT

This document has been produced with the financial assistance of the European Union (Grant no. DCI-PANAF/2020/420-028). Through the African Research Initiative for Scientific Excellence- Pilot Programme. ARISE is implemented by the African Academy of Sciences with support from the European Commission and the African Union Commission. The contents of this document are the sole responsibility of the authors and can under no circumstances be regarded as

reflecting the position of the European Union, the African Academy of Science, and African Union Commission.

REFERENCES

- Abdillah, O. B., Rus, Y. Bin, Ulfa, M., Dedi, & Iskandar, F. (2023). Recent progress on reduced graphene oxide and polypyrrole composites for high performance supercapacitors: A review. *Journal of Energy Storage*, 74(PA), 109300. <https://doi.org/10.1016/j.est.2023.109300>
- Adedjoja, O. S., Sadiku, E. R., & Hamam, Y. (2023). Prospects of Hybrid Conjugated Polymers Loaded Graphene in Electrochemical Energy Storage Applications. *Journal of Inorganic and Organometallic Polymers and Materials*, 33(12), 3915–3934. <https://doi.org/10.1007/s10904-023-02664-2>
- Aerogels, C., Wang, Z., Liu, L., Zhang, Y., Huang, Y., Liu, J., Zhang, X., Liu, X., Teng, H., & Zhang, X. (2023). A Review of Graphene-Based Materials / Polymer.
- Ana, M. D. (2022). *Graphene-Based Polymer Composites for Flexible Electronic Applications*. 1–18.
- Biswas, K. (2022). Ultrasonication mediated Iron-doped reduced graphene oxide nano-sheets exhibiting unique physico-chemical properties and biomedical applications. *Materials Chemistry and Physics*, 291(August), 126687. <https://doi.org/10.1016/j.matchemphys.2022.126687>
- Chen, S., Chen, Y., Mu, X., Wang, P., Miao, L., Tanemura, S., & Cai, H. (2023). Strategies for enhancing ionic conductivity and energy density of gel polymer electrolytes for next-generation flexible energy storage devices. *Sustainable Materials and Technologies*, 36(January), e00635. <https://doi.org/10.1016/j.susmat.2023.e00635>
- Das, T. K., & Prusty, S. (2013). *Graphene-Based Polymer Composites and Their Applications*. 319–331. <https://doi.org/10.1080/03602559.2012.751410>
- Fundamentals, S., & Applications, T. (n.d.). *Electrochemical Supercapacitors*.
- Gonçalves, G. (2022). *The Potential of rGO @ TiO₂ Photocatalyst for the Degradation of Organic Pollutants in Water*.
- Graphene in the heart of Europe. (2013). *Nature Nanotechnology*, 8(4), 221. <https://doi.org/10.1038/nnano.2013.64>
- Ibrahim, A., Klopocinska, A., Horvat, K., & Hamid, Z. A. (2021). *Graphene-Based Nanocomposites: Synthesis, Mechanical Properties, and Characterizations*.
- Itapu, B. M., & Jayatissa, A. H. (2018). A Review in Graphene / Polymer Composites. 23(3), 1–16. <https://doi.org/10.9734/CSJI/2018/41031>
- Kausar, A., Ahmad, I., Zhao, T., Aldaghri, O., Ibnaouf, K. H., & Eisa, M. H. (2023). *Graphene Nanocomposites as Innovative Materials for Energy Storage and Conversion – Design and Headways*.
- Lakra, R., Kumar, R., Sahoo, P. K., Thatoi, D., & Soam, A. (2021). A mini-review: Graphene based composites for supercapacitor application. *Inorganic Chemistry Communications*, 133(July), 108929. <https://doi.org/10.1016/j.inoche.2021.108929>
- Lee, S. J., Yoon, S. J., & Jeon, I. (2022). *Graphene / Polymer Nanocomposites : Preparation , Mechanical*.
- Moyseowicz, A., Minta, D., & Gryglewicz, G. (2023). *Conductive Polymer / Graphene-based Composites for Next Generation Energy Storage and Sensing Applications*. 202201145. <https://doi.org/10.1002/celc.202201145>
- Moyseowicz, A., Śliwak, A., Miniach, E., & Gryglewicz, G. (2017). Polypyrrole/iron oxide/reduced graphene oxide ternary composite as a binderless electrode material with high cyclic stability for supercapacitors. *Composites Part B: Engineering*, 109, 23–29. <https://doi.org/10.1016/j.compositesb.2016.10.036>
- Mustafa, Z., Ghadai, R. K., Pradhan, B. B., Swain, B. P., Biswas, J., & Kumar, D. (2024). Recent advances in polyaniline/graphene nanocomposites for supercapacitor applications:

- Synthesis, properties, and future directions. *Results in Surfaces and Interfaces*, 17(October), 100316. <https://doi.org/10.1016/j.rsurfi.2024.100316>
- Nare, R. K., Ramesh, S., Kakani, V., Haldorai, Y., Karthikeyan, C., Kumar, B. P., Siva Kumar, N., Asif, M., Kumar, S. N., Babu, D. P., Reddy, K. R., & Pasupuleti, V. R. (2024). CNTs supported NiCo₂O₄ nanostructures as advanced composite for high performance supercapacitors. *Diamond and Related Materials*, 141(October 2023), 110660. <https://doi.org/10.1016/j.diamond.2023.110660>
- Omar, F. S., Numan, A., Duraisamy, N., Bashir, S., Ramesh, K., & Ramesh, S. (2017). A promising binary nanocomposite of zinc cobaltite intercalated with polyaniline for supercapacitor and hydrazine sensor. *Journal of Alloys and Compounds*, 716, 96–105. <https://doi.org/10.1016/j.jallcom.2017.05.039>
- Paquin, F., Rivnay, J., Salleo, A., Stingelin, N., & Silva, C. (2015). Multi-phase semicrystalline microstructures drive exciton dissociation in neat plastic semiconductors. *J. Mater. Chem. C*, 3, 10715–10722. <https://doi.org/10.1039/b000000x>
- Pathak, M., Jeong, S. M., & Rout, C. S. (2023). Spinel NiCo₂O₄ based hybrid materials for supercapacitors: Recent developments and future perspectives. *Journal of Energy Storage*, 73(PA), 108881. <https://doi.org/10.1016/j.est.2023.108881>
- Pendashteh, A., Palma, J., Anderson, M., & Marcilla, R. (2015). Nanostructured porous wires of iron cobaltite: Novel positive electrode for high-performance hybrid energy storage devices. *Journal of Materials Chemistry A*, 3(32), 16849–16859. <https://doi.org/10.1039/c5ta02701b>
- Ramesh, M., Manickam, T. S., Arockiasamy, F. S., Ponnusamy, B., Sivakumar, R., Sivakumar, P., & Kandasamy, P. (2024). *Powering the Future: A Comprehensive Review of Polymer Composite Energy Storage Applications* †. 1–7.
- Ravikiran, Y. T., Chethan, B., Prasad, V., Raj Prakash, H. G., Prashantkumar, M., Tiwari, S. K., & Thomas, S. (2023). Polypyrrole/reduced graphene oxide composite as a low-cost novel sensing material for fast-response humidity sensor. *Materials Chemistry and Physics*, 303(March), 127800. <https://doi.org/10.1016/j.matchemphys.2023.127800>
- S027288422200493X. (n.d.).
- S1387700321004846. (n.d.).
- Shahid, M., Mustafa, G. M., Quader, A., Ramay, S. M., Shar, M. A., & Atiq, S. (2024). Reduced graphene oxide/ Sr₂Co₂O₅ composites as electrode material for supercapacitors. *Diamond and Related Materials*, 142(January), 110777. <https://doi.org/10.1016/j.diamond.2023.110777>
- Shankar, U., Palani, S., & Chaichana, C. (2026). Enhanced bifunctional energy applications of rGO @ Pani @ NiMgO nanocomposite: High-power pouch-type supercapacitor and efficient methanol oxidation catalysis. *Journal of Power Sources*, 666(August 2025), 239138. <https://doi.org/10.1016/j.jpowsour.2025.239138>
- Tarimo, D. J., Oyedotun, K. O., Mirghni, A. A., & Manyala, N. (n.d.). *Sulphur-reduced graphene oxide composite with improved electrochemical performance for supercapacitor applications*. 1–30.
- Tawade, A. K., Tayade, S. N., Dubal, D. P., Mali, S. S., Kook Hong, C., & Kumar K. Sharma, K. (2024). Enhanced supercapacitor performance through synergistic electrode design: Reduced graphene oxide-polythiophene (rGO-PTs) nanocomposite. *Chemical Engineering Journal*, 492(April), 151843. <https://doi.org/10.1016/j.cej.2024.151843>
- Toto, E., Laurenzi, S., & Santonicola, M. G. (2022). *Recent Trends in Graphene / Polymer Nanocomposites for Sensing Devices: Synthesis and Applications in Environmental and Human Health Monitoring*.
- Umar, A., Ahmed, F., Ullah, N., Ansari, S. A., Hussain, S., Ibrahim, A. A., Qasem, H., Kumar, S. A., Alhamami, M. A., Almehbad, N., Algadi, H., Almas, T., Selim, A. F., & Baskoutas, S. (2024). Exploring the potential of reduced graphene oxide/polyaniline (rGO@PANI)

- nanocomposites for high-performance supercapacitor application. *Electrochimica Acta*, 479(November 2023), 143743. <https://doi.org/10.1016/j.electacta.2023.143743>
- Wang, J., Li, Q., Peng, C., Shu, N., Niu, L., & Zhu, Y. (2020). To increase electrochemical performance of electrode material by attaching activated carbon particles on reduced graphene oxide sheets for supercapacitor. *Journal of Power Sources*, 450(January), 227611. <https://doi.org/10.1016/j.jpowsour.2019.227611>
- Wang, Q. (2025). *Performance and Applications Graphene / Polymer Composites*. 03001.
- Yu, C., Guo, J., Lv, S., & Jiang, X. (2023). Modified zirconia fiber/reduced graphene oxide composite aerogels with exceptional mechanical and microwave absorption properties for harsh-environment applications. *Chemical Engineering Journal*, 468(May), 143850. <https://doi.org/10.1016/j.cej.2023.143850>
- Zhang, L., Wang, Z., Xiao, F., Jiang, Y., Su, R., Yang, L., & Chen, L. (2024). Reduced graphene oxide / poly (e):aniline- co -toluidine blu Binder-free electrodes for high-performance quasi-solid-state symmetric supercapacitors. *Journal of Electroanalytical Chemistry*, 956(December 2023), 118097. <https://doi.org/10.1016/j.jelechem.2024.118097>
- Zhang, W., Wang, Y., Guo, X., Liu, Y., Zheng, Y., Zhang, M., Li, R., Peng, Z., Wang, Z., & Zhang, T. (2021). High performance Bi₂O₃/CO₃ / rGO electrode material for asymmetric solid-state supercapacitor application. *Journal of Alloys and Compounds*, 855, 157394. <https://doi.org/10.1016/j.jallcom.2020.157394>
- Zhao, C., Shu, K., Wang, C., Gambhir, S., & Wallace, G. G. (2015). Reduced graphene oxide and polypyrrole/reduced graphene oxide composite coated stretchable fabric electrodes for supercapacitor application. *Electrochimica Acta*, 172, 12–19. <https://doi.org/10.1016/j.electacta.2015.05.019>